

SBR 1500:

Application:

SBR 1500 is well suited for wide range of applications due to its unique properties. Some examples are : Tires, tread rubber and molded and extruded mechanical goods.

SBR 1502:

Application:

End uses include white sidewall tires, foot wear, light and dark colored mechanical goods and miscellaneous items where excellent physical properties and minimum discoloration and staining are required.

SBR 1712:

Application:

The SBR 1712 used for the production of tires , high quality technical rubber goods, moulded and extruded mechanical rubber goods and other industrial products where colour and staining are not decisive factors.

Grade	Moony viscosity Raw (ML 1+4@100 0C)	Oil Content (%)	Bound Styrene (%)
SBR 1500	46-58		22.5-24.5
SBR 1502	46-58		
SBR 1712	42-52	22.5-28.5	22.5-24.5
SBR 0202	40-50		44-48